

## Product Information

### Product description

INNOPOL® CS 3-7120 is a 20% talc-filled polypropylene compound. This grade is available in nature and custom coloured form.

### Recommended application

INNOPOL® CS 3-7120 is recommended especially for producing products, where good stiffness and also impact resistance are required besides long term heat stability.

Physical properties / Typical values	Test method	Unit	Mean value
<b>Properties</b>			
Abbreviated term	ISO 1043	-	PP TD20
Colour	-	-	natural
Density 23°C	ISO 1183	g/cm <sup>3</sup>	1.04
<b>Rheology</b>			
Melt Volume Flow Rate MVR (230°C/5kg)	ISO 1133	cm <sup>3</sup> /10 min	10±3
Ash content 600°C	ISO 3451	%	20±2
<b>Mechanical properties</b>			
Tensile Modulus (1 mm/min)	ISO 527-1,-2	MPa	2400
Tensile Stress at Yield (50 mm/min)	ISO 527-1,-2	MPa	27
Tensile Strain at Yield (50 mm/min)	ISO 527-1,-2	%	5,3±0,8
Stress at Break (1A/50)	ISO 527-1,2	MPa	23±3
Impact Strength Charpy 23°C	ISO 179/1eU	kJ/m <sup>2</sup>	45
Notched Impact Strength Charpy 23°C	ISO 179/1eA	kJ/m <sup>2</sup>	4,5±0,8
Notched Impact Strength Charpy -30°C	ISO 179/1eA	kJ/m <sup>2</sup>	2
Flexural Modulus (2 mm/min)	ISO 178	MPa	2700
<b>Thermal properties</b>			
Vicat Softening Point, A120	ISO 306	°C	152
Heat Deflection Temperature 0,45 MPa(HDT/B)	ISO 75-1,-2	°C	119

Data contain above represent typical values of individual properties. They are informative, please do not construe as specifications.

MFR is measured at 230°C under a load of 2.16 kg with standard nozzle having a diameter of 2.095 mm.

Average mechanical property values of several measurements carried out on standard injection moulded specimens (ISO 3167) conditioned at room temperature (ISO 291).

### Physical form and storage

Standard packaging includes the 25 kg bags, the 1000 kg octabin (octagonal container) or the 1250 kg big-bag. All containers are tightly sealed and should be opened only immediately prior to processing.

INNOPOL® CS 3-7120 should generally have a moisture content of less than 0.07% when being processed. In order to ensure reliable production pre-drying is suggested before processing of material at 80°C/2h.

INNOPOL® CS 3-7120 should be stored in dry conditions at temperatures below 60 °C and protected from UV-light. The quality of product may suffer due to storage under improper condition.

## Product Information

### Recommended processing parameters

The following parameters should be used as guidelines:

Barrel temperatures	190 – 230°C
Polymer melt temperature	220 – 240°C
Mould temperature	10 – 50°C
Injection speed	intermediate or slow, depend on the mould design
Hold pressure	50 – 100 % of actual injection pressure

### Product safety

For detailed safety information, see Safety Data Sheet, which is available on request.

### Note

All information provided herein is based on our best knowledge, experience and laboratory test results. However, Inno-Comp Kft. shall be in no even responsible or liable for misunderstood data or for inefficient application.

In order to check the availability of products, please, contact us:

### INNO-COMP KFT.

H-3580 Tiszaújváros, Vegyészek útja 8.

Telephone: +36-49-542-084

Fax: +36-49-522-509

E-mail: [innocomp@innocomp.hu](mailto:innocomp@innocomp.hu)