

## Product Information

### Product description

INNOPOL® CS 3-3120 is a 20% talcum filled polypropylene compound. This grade is available in nature and custom coloured form.

### Recommended application

INNOPOL® CS 3-3120 is recommended for producing injection moulded products where the required property is high strength besides good stiffness.

Physical properties / Typical values	Test method	Unit	Mean value
<b>Properties</b>			
Abbreviated term	ISO 1043	-	PP TD20
Colour	-	-	nature
Density 23°C	ISO 1183	g/cm <sup>3</sup>	1,05
<b>Rheology</b>			
Melt Mass Flow Rate MFR (230°C/2,16kg)	ISO 1133	g/10 min	10
<b>Mechanical properties</b>			
Tensile Modulus (1 mm/min)	ISO 527-1,-2	MPa	2600
Tensile Stress at Yield (50 mm/min)	ISO 527-1,-2	MPa	30
Tensile Strain at Yield (50 mm/min)	ISO 527-1,-2	%	5
Notched Impact Strength Charpy 23°C	ISO 179/1eA	kJ/m <sup>2</sup>	3,5
Notched Impact Strength Charpy -20°C	ISO 179/1eA	kJ/m <sup>2</sup>	2
Flexural Modulus (2 mm/min)	ISO 178	MPa	2800
<b>Thermal properties</b>			
Heat Deflection Temperature 0.45 MPa (HDT/B)	ISO 75-1.-2	°C	125

Data contain above represent typical values of individual properties. They are informative, please do not construe as specifications.

MFR is measured at 230°C under a load of 2.16 kg with standard nozzle having a diameter of 2.095 mm.

Average mechanical property values of several measurements carried out on standard injection moulded specimens (ISO 3167) conditioned at room temperature (ISO 291).

### Physical form and storage

Standard packaging includes the 25 kg bags, the 1000 kg octabin (octagonal container) or the 1250 kg big-bag. All containers are tightly sealed and should be opened only immediately prior to processing.

INNOPOL® CS 3-3120 should generally have a moisture content of less than 0.07% when being processed. In order to ensure reliable production pre-drying is suggested before processing of material at 80°C/2h.

INNOPOL® CS 3-3120 should be stored in dry conditions at temperatures below 60 °C and protected from UV-light. The quality of product may suffer due to storage under improper condition.

## Product Information

### Recommended processing parameters

The following parameters should be used as guidelines:

Barrel temperatures	210 – 240°C
Polymer melt temperature	230 – 250°C
Mould temperature	15 – 50°C
Injection speed	medium
Hold pressure	50 – 100 % of maximum injection pressure

### Product safety

For detailed safety information, see Safety Data Sheet, which is available on request.

### Note

All information provided herein is based on our best knowledge, experience and laboratory test results. However, Inno-Comp Kft. shall be in no even responsible or liable for misunderstood data or for inefficient application.

In order to check the availability of products, please, contact us:

### INNO-COMP KFT.

H-3580 Tiszaújváros, Vegyészek útja 8.

Telephone: +36-49-542-084

Fax: +36-49-522-509

E-mail: [innocomp@innocomp.hu](mailto:innocomp@innocomp.hu)